



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

DAP® TOUCH 'N SEAL® QUICK CURE FOAM SEALANT – Cream

PRODUCT DESCRIPTION

DAP® Touch 'n Seal® Quick Cure foam is a high performance, 1-component, sealant ideal for quickly filling gaps and voids to block out air drafts, moisture, and insects. Quick Cure is Class 1 fire rated and bonds to common building materials including wood, concrete, insulating foam boards, metal, plastics, and dry wall. Quick cure won't shrink and helps lower energy costs. Quick Cure cannister sealants are available in High Yield (HY) and Reduced Expansion (RX) formulations.



PACKAGING	Case	COLOR	UPC
10 lb Cylinder (HY)	1	Cream	7565000062
10 lb Cylinder (RX)	1	Cream	7565000063
16 lb Cylinder (HY)	1	Cream	7565000064
16 lb Cylinder (RX)	1	Cream	7565000065

KEY FEATURES & BENEFITS

- High Yield (HY) and Reduced Expansion (RX) Formulas
- Weather-resistant bond seals out drafts and moisture
- Physically blocks insects and other pests
- Paintable / sandable
- Saves energy
- ICC-ES ESR 1926
- Interior / exterior use



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

SUGGESTED USES

USE TO FILL AND SEAL:

- Through-penetrations
- Gaps and cracks in foundations, crawlspaces, attics, and basements
- Partitions and stud walls
- Top and bottom of stair stringer
- Space connections in soffits and drop ceilings
- Concrete slabs
- Sill plates
- Rim joists

FOR BEST RESULTS

- Apply in temperatures between 60°F- 100°F (16°C – 38°C)
- Surface must be clean, dry, and free of all foreign material for adhesion
- If used outdoors, paint to avoid foam discoloration
- Use around, not inside, junction boxes

APPLICATION

DIRECTIONS: Important – read all directions and cautions before use. Always wear gloves, eye protection and work clothes. Use drop cloths. Product is flammable during dispensing – turn off sources of ignition prior to use. Always refer to local building codes prior to application of Touch n' Seal sealants. **CYLINDER MAY BURST IF LEFT IN HOT VEHICLE, EXPOSED TO DIRECT SUNLIGHT OR TEMPERATURES ABOVE 122°F (50°C).**

Preparation / Application: To promote adhesion, surface must be clean, dry, and free of all foreign material. Check expiration date on carton to ensure product is current. Chemical contents must be 70°F – 90°F (21°C – 32°C) before dispensing. Application in lower/higher temperatures may alter set-up / cure time, yield, density, physical properties, and reduce overall performance. Do not expose to heat, sparks or open flames. Remove cylinder from carton and shake about 10 times; stand upright. With applicator in closed position, attach hose to wand and cylinder valve. Tighten fittings with open-end wrench; do not over-tighten. Open cylinder valve and move wand lever to open position, regulating flow rate with lever. Dispense on scrap material first, then fill voids about 40% full, leaving room for foam to expand.

Clean-up: If wet foam contacts skin, clean immediately with a dry rag – do not use water – water accelerates curing. Cured foam must be removed mechanically from surfaces. Uncured foam can be cleaned from most surfaces with Foam Cleaner or acetone. If foam dries on skin, apply generous amounts of petroleum jelly, put on plastic gloves and wait 1 hour. With a clean cloth, firmly wipe off residue and repeat process if necessary. **DO NOT** use acetone or other solvents to remove product from skin.



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

Storage & Disposal. Keep container tightly closed in a cool, well-ventilated area. Store upright below 90°F (33°C). Do not expose containers to conditions that may damage, puncture, or burst the containers. Dispose of leftover material / containers in accordance with Federal, state, and local regulations. See SDS for more information.

TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Yield (3/8" bead) ASTM C1536	10 lb. HY – 4460 In ft 16 lb HY – 7763 In ft 10 lb RX – 4341 In ft 16 lb RX – 6974 In ft
Dry Time/ Tack Free @ 72°F / 50% R. H.	< 15 minutes
Cure Time @ 72°F / 50% R. H.	24 hours
Shelf Life	18 months (unopened)
Application Temperature Range	50°F to 100°F (10°C ~ 38°C)
Cutable	< 1 hour
International Building Code	Compliant
International Residential Code	Compliant
BOCA National Building Code	Compliant
ICC-ES	ESR-1926
UL Classified Caulking & Sealants	Listed
UL 723 Surface Burning Characteristics Fire Test (Flame/Smoke)	20/20

SAFETY

See product label or Safety Data Sheet (SDS) for health and safety information. You can request an SDS by visiting our website at dap.com or calling 888-DAP-TIPS.

WARRANTY

LIMITED WARRANTY: If the product fails to perform when used as directed, within one year from the date of purchase, call 888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund. DAP Products Inc. will not be responsible for incidental or consequential damages.



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

COMPANY IDENTIFICATION

Manufacturer: DAP Products Inc., 2400 Boston Street, Baltimore, Maryland 21224

Usage Information: Call 888-DAP-TIPS or visit dap.com & click on "Ask the Expert"

Order Information: 800-327-3339 or orders@dap.com

Fax Number: 410-558-1068

Also, visit the DAP website at dap.com

R14175
1L15



UNDERWRITERS LABORATORIES INC.
CLASSIFIED CAULKING AND SEALANT
Surface Burning Characteristics
Applied To Inorganic Reinforced
Cement Board*
Flame Spread 20 Smoke
Developed 20

*TESTED AS APPLIED IN THREE ½" DIAMETER
BEADS 5" ON CENTER COVERING 8.3% OF THE
EXPOSED TEST SAMPLE AREA.