



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

DAP® CONSTRUCTION ADHESIVE Multi Purpose

PRODUCT DESCRIPTION

DAP® CONSTRUCTION ADHESIVE Multi Purpose is designed to bond common building materials. This easy to apply formula meets ASTM C557 and provides a weather resistant bond once fully cured.



PACKAGING	COLOUR	UPC
266ml (9 fl oz.) Cartridge	White	7079874883

KEY FEATURES & BENEFITS

- Easy Water Clean Up
- Low Odour
- Easy to Gun
- VOC Compliant

PERFORMANCE CHARACTERISTICS

- Meets ASTM C557 specification for drywall installation
- Interior use

SUGGESTED USES

Adheres to:

- Brick /Masonry/ Concrete
- Drywall / Foamboard
- Ceramic Tiles
- Cove Base
- Dimensional Lumber
- Plywood / OSB/ FRP



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

FOR BEST RESULTS

- Apply in temperatures above 4°C. Keep adhesive above 4°C for easier gunning.
- For square surfaces apply around perimeter and “X” shaped bead. For long surfaces use “S” shaped bead. Press firmly into place. One surface must be porous.
- Store away from extreme heat or cold.

APPLICATION

1. Surfaces must be clean, structurally sound, and free of debris.
2. Pre-cut and fit materials before applying adhesive.
3. Trim nozzle to desired bead size. 6 mm (1/4”) recommended for most applications.
4. Load cartridge into applicator gun.
5. Apply a continuous bead to desired surface.
6. Within 10 minutes, position and press substrates firmly into place.
7. Certain applications may require mechanical fasteners.
8. Allow to dry for 48 hours

TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Typical Uncured Physical Properties	
Base Polymer:	Acrylic Latex
Bead Colour	Tan
Weight % Solids	68%
Odour	Mild
Clean Up	Soap & Water
Flash Point	26°C
Shelf Life	18 months
Coverage	6mm (1/4”) bead yields 8.2m (27 linear ft.), 9mm (3/8”) bead yields 3.6m (12 linear ft).
Typical Application Properties	
Application Temperature Range:	4°C – 37°C
Tooling Time (Working Time)	15 minutes
Full Cure Time	48 hours
Typical Cured Performance Properties	
Service Temperature Range:	-17°C to 60°C



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

VOC Less Exempt Less Water

VOC less Water,
less Exempt Solvent: <32 g/L

CLEAN UP & STORAGE

Uncured adhesive: wash away with warm water and soap. Cured adhesive: must be cut or scraped away. Clean hands and tools with warm water and soap. Store container in a cool, dry place away from extreme heat or cold.

SAFETY

See product label or Safety Data Sheet for health and safety information. You can request an SDS sheet by calling 888-DAP-TIPS or by visiting our website at dap.ca.

WARRANTY

If product fails to perform as directed, within one year from the date of purchase, call 1-888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund. DAP will not be liable for incidental or consequential damages.

COMPANY IDENTIFICATION

Manufactured for: DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON, M1X 1B7

Usage Information: Call 888-DAP-TIPS or visit dap.ca & click on "Ask the Expert"

Order Information: 800-668-9397 or 416-321-1522

Fax Number: 416-321-3325

Also visit the DAP website at dap.ca